



5005

(EN AW-5005)

Chemical composition	Al	Cu	Mg	Mn	Fe	Si	Zn	Cr
% Present (Max)	Balance	0.20	0.50-1.10	0.20	0.70	0.03	0.25	0.10

5005 is a medium-strength aluminium alloy with excellent formability and good anodising properties. It is widely used in architectural applications, signage, and general sheet metal fabrication.

Note: Values are in accordance with EN 573 specifications. Actual mill certs available upon request.

