



825

(UNS N08825) W. Nr. 2.4858

Chemical composition	Ni	Cr	Fe	Mo	Ti	Cu
% Present (Max)	38.0-46.0	19.5-23.5	Bal	2.50-3.50	0.60-1.20	1.50-3.0

Incoloy 825 provides outstanding resistance to sulfuric and phosphoric acids as well as chloride stress corrosion cracking. Ideal for chemical processing, oil & gas, and pollution control equipment.

Note: Values are in accordance with AMS/EN specifications. Actual mill certs available upon request.

