



600

(UNS N06600) W. Nr. 2.4816

Chemical composition	Ni	Cr	Fe	C	Mn	Si	Cu
% Present (Max)	72	14.0-17.0	6.0-10.0	0.15	1.0	0.50	0.50

Inconel 600 offers excellent corrosion and oxidation resistance at high temperatures. Widely used in chemical processing, heat exchangers, and furnace components.
Note: Values are in accordance with AMS/EN specifications. Actual mill certs available upon request.

Note: Values are in accordance with EN 10088 specifications. Actual mill certs available upon request.

