



601

(UNS N06601) W. Nr. 2.4851

Chemical composition	Ni	Cr	Fe	C	Al
% Present (Max)	58.0-63.0	21.0-25.0	Bal	0.10	1.0-1.70

Inconel 601 provides superior high-temperature oxidation resistance and remains stable under thermal cycling. Ideal for radiant tubes, heat treatment baskets, and furnace applications.

Note: Values are in accordance with EN 10088 specifications. Actual mill certs available upon request.

